



## Multi-form Threadmilling Guide

Series: 8429xx, 9871xx

Multi-Form Thread Mills are a fast way to threadmill a part. Since they use the entire length of cut in a helical interpolation environment, specific machining parameters are needed to avoid deflection and breakage. These tools can be used successfully in materials ranging from Aluminum up to and including Hardened Steels.

### Speeds & Feeds calculations:

1. Determine the correct SFM and Chip Load (IPT) for the cutter and material
2. Calculate the Speed (RPM) and Linear Feed (IPM)
3. Adjust Linear Feed to account for helical interpolation of internal or external threads
4. Determine correct number of radial passes at full axial depth

Example: Tool #987154 to machine a 5/16-18 internal thread in 17-4 stainless steel

1. From Speeds & Feeds chart (next page), SFM is 200 and Chip Load (IPT) is .00048
2. Calculate Speed (RPM) and Linear Feed (IPM)

$$\begin{aligned} \text{RPM} &= (\text{SFM} \times 3.82) / \text{Cutter Diameter} \\ &= (200 \times 3.82) / .245 \\ &= 3118 \end{aligned}$$

$$\begin{aligned} \text{Linear Feed (IPM)} &= \text{RPM} \times \text{IPT} \times \text{Number of Flutes} \\ &= 3118 \times .00048 \times 3 \\ &= 4.5 \end{aligned}$$

3. Adjust Linear Feed (use Table 1 to determine Major Thread Diameter)

$$\begin{aligned} \text{Adj Internal Feed} &= [(\text{Major Thread Dia} - \text{Cutter Dia}) / \text{Major Thread Dia}] \times \text{Linear Feed} \\ &= [(.312 - .245) / .312] \times 4.5 \\ &= .9 \end{aligned}$$

$$\begin{aligned} \text{Adj External Feed} &= [(\text{Major Thread Dia} + \text{Cutter Dia}) / \text{Major Thread Dia}] \times \text{Linear Feed} \\ &= [(.312 + .245) / .312] \times 4.5 \\ &= 8.0 \end{aligned}$$

4. Determine Number of Radial Passes using Table 1

- For Easy Machinability = 3 Radial Pass at full Axial Depth
- For Moderate Machinability = 3 Radial Passes at full Axial Depth
- For Difficult Machinability = 4 Radial Passes at full Axial Depth

#### Definitions:

- Easy Machinability materials include Non-Ferrous alloys and Lead Steels
- Moderate Machinability materials include 200/300/400 Stainless Steels and Steels up to 35 Rc
- Difficult Machinability materials include Inconel, Titanium and Steels 36-45 Rc

5. Conclusion

In this example, the tool would run at 3118 RPM, .9 IPM and make 3 Radial Passes

### Setup & Use:

1. Check software and input proper feed values (Linear or Adjusted)
2. Choke up on tool
3. Minimize runout (consider entire system of spindle, collet, holders etc)
4. Minimize all vibration (consider tool holding, work holding, rpm "sweet spot" etc)
5. To break in the tool, reduce feed rates by 75% on the first one to two holes
6. Cutter should engage part using an arcing toolpath to avoid shock loading (see Table 2)
7. Climb mill for best finish and tool life (see Table 2)
8. Flush chips with coolant to avoid recutting

Thread Size	Major Thread Diameter	Number of Radial Passes		
		Easy	Moderate	Difficult
		Machinability	Machinability	Machinability
0-80	0.060	3	4	5
1-64	0.073	3	4	5
2-56	0.086	3	4	4
3-48	0.099	3	4	4
4-40	0.112	3	4	4
5-40	0.125	3	4	4
5-44	0.125	3	4	4
6-32	0.138	3	3	4
8-32	0.164	3	3	4
8-36	0.164	2	3	3
10-24	0.190	3	3	4
10-28	0.190	2	3	3
10-32	0.190	2	3	3
12-24	0.216	3	3	4
12-28	0.216	2	3	3
1/4-20	0.250	3	3	4
1/4-28	0.250	2	2	3
5/16-18	0.312	3	3	4
5/16-24	0.312	2	2	3
3/8-16	0.375	3	3	4
3/8-24	0.375	2	2	3
7/16-14	0.437	3	3	4
7/16-20	0.437	2	2	3
1/2-13	0.500	3	3	4
1/2-20	0.500	2	2	3
9/16-12	0.562	3	3	4
9/16-18	0.562	2	3	3
5/8-11	0.625	3	3	4
5/8-18	0.625	2	3	3
3/4-10	0.750	3	3	4
3/4-12	0.750	2	3	1
3/4-16	0.750	2	3	3
7/8-9	0.875	3	3	4
7/8-14	0.875	2	3	3
1-8	1.000	3	4	5
1-12	1.000	3	3	3
1-14	1.000	3	3	3
<b>NPT</b>				
1/16-27	0.312	2	2	3
1/8-27	0.405	2	2	3
1/4-18	0.540	2	2	3
3/8-18	0.675	2	2	3
1/2-14	0.840	2	3	4
3/4-14	1.050	2	3	4
1-11.5	1.315	2	3	4
2-11.5	2.375	2	3	4
<b>METRIC</b>				
M4.5 x .75	.177 (4.5mm)	2	3	3
M5 X .8	.197 (5mm)	2	3	3
M6 X .75	.236 (6mm)	2	3	3
M6 X 1	.236 (6mm)	2	3	3
M8 X .75	.315 (8mm)	2	3	3
M8 X 1.25	.315 (8mm)	3	3	4
M10 X 1	.394 (10mm)	2	2	3
M10 X 1.5	.394 (10mm)	3	3	4
M12 X 1	.472 (12mm)	2	2	3
M12 X 1.75	.472 (12mm)	3	3	4
M14 X 1.5	.551 (14mm)	2	3	3
M14 X 2.0	.551 (14mm)	3	3	4
M16 X 1	.630 (16mm)	2	3	3
M16 X 2.0	.630 (16mm)	3	3	4
M18 X 1.5	.709 (18mm)	2	3	3
M18 X 2	.709 (18mm)	3	3	4
M20 X 2.5	.787 (20mm)	3	3	4

Table 2	
<p><b>INTERNAL, RIGHT HAND THREAD (CLIMB MILLING)</b></p> <p>Step 1-2: Cutter moves into position Step 2-3: Cutter engages part with arcing tool path while "Z" feeds up from bottom Step 3-4: Cutter moves helically one rotation Step 4-5: Cutter exits part along arcing tool path while maintaining "Z" feed Step 5-6: Cutter returns to center</p>	
<p><b>INTERNAL, LEFT HAND THREAD (CLIMB MILLING)</b></p> <p>Step 1-2: Cutter moves into position Step 2-3: Cutter engages part with arcing tool path while "Z" feeds down from top Step 3-4: Cutter moves helically one rotation Step 4-5: Cutter exits part along arcing tool path while maintaining "Z" feed Step 5-6: Cutter returns to center</p>	
<p><b>EXTERNAL, RIGHT HAND THREAD (CLIMB MILLING)</b></p> <p>Step 1-2: Cutter engages part with arcing tool path while "Z" feeds down from top Step 2-3: Cutter moves helically one rotation Step 3-4: Cutter exits part along arcing tool path while maintaining "Z" feed</p>	
<p><b>EXTERNAL, LEFT HAND THREAD (CLIMB MILLING)</b></p> <p>Step 1-2: Cutter engages part with arcing tool path while "Z" feeds up from bottom Step 2-3: Cutter moves helically one rotation Step 3-4: Cutter exits part along arcing tool path while maintaining "Z" feed</p>	

MATERIAL	Hardness: ≤ 28 Rc (≤ 271 HBn)												
	SFM	Chip Load (IPT) By Cutter Diameter											
		0.047	0.062	0.078	0.093	0.125	0.187	0.250	0.312	0.375	0.500	0.625	0.750
<b>ALUMINUM ALLOYS</b>													
Casting (2xx, 5xx, 7xx, 8xx)	750	.00012	.00016	.00020	.00024	.00032	.00067	.00090	.00137	.00165	.00220	.00275	.00330
Wrought (1xxx, 2xxx, 3xxx, 5xxx, 6xxx, 7xxx, 8xxx)	1200												
Casting - 3%-5% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	750												
Casting - 5%-8% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	700												
Casting - 8%-12% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	650	.00011	.00014	.00018	.00021	.00029	.00061	.00081	.00124	.00149	.00198	.00248	.00297
Casting - 12%-16% Si (3xx, A3xx, C3xx, 4xx, A4xx, B4xx)	475												
Wrought - 5%-8% Si (4xxx)	1000												
Wrought - 8%-12% Si (4xxx)	800												
<b>MAGNESIUM ALLOYS</b>	1500	.00012	.00016	.00020	.00024	.00032	.00067	.00090	.00137	.00165	.00220	.00275	.00330
<b>ZINC ALLOYS</b>	800												
<b>COPPER ALLOYS</b>													
High Coppers - 90%+ (C1xxx)	450												
Brass (Copper Zinc alloys, C2xxx, C3xxx, C4xxx, C6400-C69800)	1000												
Phosphor Bronzes (Copper Tin alloys, C5xxx)	450												
Aluminum Bronzes (Copper Aluminum alloys, C6900-C64200)	600	.00012	.00015	.00019	.00023	.00031	.00055	.00073	.00115	.00138	.00184	.00231	.00277
Silicon Bronzes (Copper Silicon alloys, C64700-C66100)	1000												
Copper Nickels, Nickel Silvers (Copper Nickel alloys, C7xxx)	450												
Cast Copper Alloys (C83300-C86200, C86400-C87900, C9200-C95800, C97300-C97800, C99400-C99700)	1000												



Speeds & Feeds

**Product Table:** Thread Milling Cutters - Multi-Form - Long Flute - Metric  
**Series:** 8429xx, 9871xx

**Hardened Steels:**

**For 46-54 Rc:**  
 130 SFM, 75% of IPT (from 29-37 Rc section)  
 3-4 Radial Passes at full Axial Depth

**For 55-60 Rc:**  
 80 SFM, 50% of IPT (from 29-37 Rc section)  
 4-5 Radial Passes at full Axial Depth

**Please note:**

All posted speed and feed parameters are suggested starting values that may be increased given optimal setup conditions. Chip loads reflect uncoated cutters and may be increased 5%-10% if coated. For ferrous materials with hardness ≤ 28 Rc, chip loads can be increased 3%-5%.

If you require additional information, Harvey Tool has a team of technical experts available to assist you through even the most challenging applications. Please contact us at **800-645-5609** or [Harveytech@harveyperformance.com](mailto:Harveytech@harveyperformance.com).

WARNING: Cutting tools may shatter under improper use. Government regulations require use of safety glasses and other appropriate safety equipment in the vicinity of use.

MATERIAL	Hardness: 29-37 Rc (279-344 HBn)												
	SFM	Chip Load (IPT) By Cutter Diameter											
		0.047	0.062	0.078	0.093	0.125	0.187	0.250	0.312	0.375	0.500	0.625	0.750
<b>CARBON STEELS</b>													
Free-Machining/Low Carbon steels, 10xx - 1029 & all 10Lxx, 11xx - 1139 & all 11Lxx, 12xx - 1215 & all 12Lxx	550	.00009	.00012	.00015	.00018	.00024	.00054	.00072	.00112	.00135	.00180	.00225	.00270
1030 - 1095, 1140 - 1151, 13xx, 15xx, 2xx, 3xx, 4xx & 4Lxx, 5xxx & 5Lxx, 51xxx & 50Lxx, 51xxx & 51Lxx, 52xxx & 52Lxx, 6xxx, 8xxx, 9xxx	450	.00009	.00012	.00015	.00018	.00024	.00054	.00072	.00100	.00120	.00160	.00200	.00240
<b>STAINLESS STEELS</b>													
203 EZ, 303 (all types), 416, 416Se, 416 Plus X, 420F, 420FSe, 430F, 430FSe, 440F, 440FSe	400	.00009	.00012	.00015	.00018	.00024	.00054	.00072	.00112	.00135	.00180	.00225	.00270
201, 202, 203, 205, 301, 302, 304, 304L, 308, 309, 310, 314, 316, 316L, 317, 321, 329, 330, 347, 348, 385, 403, 405, 409, 410, 413, 420, 429, 430, 434, 436, 442, 446, 501, 502	350	.00009	.00012	.00015	.00018	.00024	.00036	.00048	.00075	.00090	.00120	.00150	.00180
414, 431, 440A, 440B, 440C, 13-8, 15-5, 15-7, 17-4, 17-7	200	.00009	.00012	.00015	.00018	.00024	.00036	.00048	.00067	.00081	.00108	.00135	.00162
<b>TOOL STEELS</b>													
A, L, O, P, W series	325	.00010	.00013	.00016	.00020	.00026	.00039	.00053	.00088	.00106	.00141	.00176	.00211
D, H, M, T, S series	225	.00009	.00012	.00015	.00018	.00024	.00036	.00048	.00080	.00096	.00128	.00160	.00192
<b>TITANIUM ALLOYS</b>	275	.00010	.00013	.00016	.00020	.00026	.00039	.00053	.00077	.00092	.00123	.00154	.00185
<b>HIGH TEMP ALLOYS</b>													
Inconel, Hastelloy, Waspalloy, Monel, Nimonic, Haynes, Discoloy, Incoloy	90	.00008	.00011	.00014	.00016	.00022	.00033	.00044	.00065	.00078	.00104	.00130	.00156

MATERIAL	Hardness: 38-45 Rc (353-421 HBn)												
	SFM	Chip Load (IPT) By Cutter Diameter											
		0.047	0.062	0.078	0.093	0.125	0.187	0.250	0.312	0.375	0.500	0.625	0.750
-	-	-	-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-	-	-	-	-
-	-	-	-	-	-	-	-	-	-	-	-	-	-
200	.00008	.00010	.00013	.00015	.00020	.00031	.00041	.00064	.00077	.00102	.00128	.00153	
160	.00008	.00010	.00013	.00015	.00020	.00031	.00041	.00057	.00069	.00092	.00115	.00138	
200	.00008	.00011	.00014	.00017	.00022	.00034	.00045	.00075	.00090	.00120	.00150	.00180	
180	.00008	.00010	.00013	.00015	.00020	.00031	.00041	.00068	.00082	.00109	.00136	.00163	
150	.00008	.00011	.00014	.00017	.00022	.00034	.00045	.00065	.00079	.00105	.00131	.00157	
70	.00007	.00009	.00012	.00014	.00019	.00028	.00037	.00055	.00066	.00088	.00111	.00133	