



Speeds & Feeds

Product Table: Miniature High Performance Drills - Hardened Steels
Characteristics: 8x-10x Length of Flute
Series: ARYxxx-C6, DXTxxx-C6

Product Notes:

- Pecking cycles are recommended to avoid chip packing and breakage.
- For ferrous materials at 38-45 Rc, 1-2x Diameter is recommended for an initial peck, and each subsequent peck should be .5-1x Diameter.
- For harder steels at > 45 Rc, .5-1x Diameter peck depth is recommended.

General notes:

All posted speed and feed parameters are suggested starting values that may be increased given optimal setup conditions.

If you require additional information, Harvey Tool has a team of technical experts available to assist you through even the most challenging applications. Please contact us at **800-645-5609** or Harveytech@harveyperformance.com.
 WARNING: Cutting tools may shatter under improper use. Government regulations require use of safety glasses and other appropriate safety equipment in the vicinity of use.

Material	Hardness	SFM	Chip Load (IPR - Inches per Revolution) By Drill Diameter								
			.015	.031	.047	.062	.078	.093	.125	.187	.250
Hardened Steels	38-45 Rc	150	.00022	.00045	.00068	.00089	.00112	.00134	.00180	.00269	.00360
	45-55 Rc	90	.00016	.00033	.00051	.00067	.00084	.00100	.00135	.00202	.00270
	56-68 Rc	40	.00011	.00022	.00034	.00045	.00056	.00067	.00090	.00135	.00180